Exhibit 33

TO: Bob Ainsworth
Steve Schaible

From Larry Wasicek

Attached is Tinius Olson data that I took on the PEEK extrusion that had different air gaps.

The interesting portion of this data, in my opinion, is the slope data. **This information is reference data only.** FYI, the machine did not have a current calibration sticker on it. Also this information will not be contained in a lab book or formal report.

Any questions give me a call.

Take Care.

CC: Dan Cox

PEEK/AIR/.3"

Description	PEEK
Lot #	AIR GAP FOR DIE .3"
Operator and date	LARRY WASICEK 5/19/94

Enter in moment weight	0.045
Enter in inherent weight	0.005
Enter in span	0.5

Note:
Inherent weight is .1 for 6" machine
Inherent weight is .005 for 1" machine

Raw Bending Data

samples

		#1	#2	#3	#4	#5		Avg.	Std.Dev.
	0	1	1	1	1	1	0	1.0	0.0
	3	6	7	7	7	8	3	7.0	0.7
Degrees	6	12	12	14	12	14	6	12.8	1.1
	9	18	18	20	19	20	9	19.0	1.0
	12	22	23	25	24	24	12	23.6	1.1
	15	26	26	28	27	27	15	26.8	0.8
Kink angle		28	28	31	29	28		28.8	1.3
Slope (3,6,9) ref.		2.0000	1.8333	2.1667	2.0000	2.0000		2.0000	
Slope (0,3,6,9)		1.9000	1.8667	2.1333	1.9667	2.1000		1.9933	
Inner diameter		.0325	.0325	.0325	.0325	.0325		.0325	
Outer diameter		.0370	.0370	.0370	.0370	.0370		.0370	
E (4PT)		243700	239400	273600	252200	269300		255600	

PEEK/AIR/1.25"

Description	PEEK
Lot #	AIR GAP FOR DIE 1.25"
Operator and date	LARRY WASICEK 5/19/94

Enter in moment weight	0.045
Enter in inherent weight	0.005
Enter in span	0.5

Note:
Inherent weight is .1 for 6" machine
Inherent weight is .005 for 1" machine

Raw Bending Data

		samples							
		#1	#2	#3	#4	#5		Avg.	Std.Dev.
	0	1	1	1	1		0	1.0	0.0
	3	8	8	8	8		3	8.0	0.0
Degrees	6	15	16	15	15		6	15.3	0.5
	9	21	23	23	22		9	22.3	1.0
	12	27	28	28	26		12	27.3	1.0
	15	31	34	34	29		15	32.0	2.4
Kink angle		37	39	37	30			35.8	3.9
Slope (3,6,9) ref.		2.1667	2.5000	2.5000	2.3333			2.3750	
Slope (0,3,6,9)		2.2333	2.4667	2.4333	2.3333			2.3667	
Inner diameter		.0310	.0310	.0310	.0310			.0310	
Outer diameter		.0385	.0385	.0385	.0385			.0385	
E (4PT)		170600	188400	185800	178200			180800	

PEEK/AIR/3.5

Description	PEEK
Lot #	AIR GAP FOR DIE 3.5"
Operator and date	LARRY WASICEK 5/19/94

Enter in moment weight	0.045
Enter in inherent weight	0.005
Enter in span	0.5

Note:
Inherent weight is .1 for 6" machine
Inherent weight is .005 for 1" machine

Raw Bending Data

		samples							
		#1	#2	#3	#4	#5		Avg.	Std.Dev.
	0	1	1	1	1	1	0	1.0	0.0
	3	7	6	7	7	7	3	6.8	0.4
Degrees	6	13	12	13	13	13	6	12.8	0.4
	9	19	18	18	18	19	9	18.4	0.5
	12	23	23	24	24	24	12	23.6	0.5
	15	27	27	28	28	29	15	27.8	0.8
Kink angle		34	33	39	39	35		36.0	2.8
Slope (3,6,9)	ref.	2.0000	2.0000	1.8333	1.8333	2.0000		1.9333	
Slope (0,3,6,9)		2.0000	1.9000	1.9000	1.9000	2.0000		1.9400	
Inner diameter		.0295	.0295	.0295	.0295	.0295		.0295	
Outer diameter		.0355	.0355	.0355	.0355	.0355		.0355	
E (4PT)		234100	222400	222400	222400	234100		227100	

Description	PEEK
Lot #	AIR GAP FOR DIE 17"
Operator and date	LARRY WASICEK 5/19/94

Enter in moment weight	0.045
Enter in inherent weight	0.005
Enter in span	0.5

Note:
Inherent weight is .1 for 6" machine
Inherent weight is .005 for 1" machine

Raw Bending Data

samples

		#1	#2	#3	#4	#5		Avg.	Std.Dev.
	0	1	1	1	1		0	1.0	0.0
	3	6	7	7	6		3	6.5	0.6
θegrees	6	13	13	13	12		6	12.8	0.5
	9	19	18	19	17		9	18.3	1.0
	12	23	23	23	22		12	22.8	0.5
	15	27	27	27	26		15	26.8	0.5
Kink angle		32	32	31	28			30.8	1.9
Slope (3,6,9) ref.		2.1667	1.8333	2.0000	1.8333	#VALUE!		1.9583	
Slope (0,3,6,9)		2.0333	1.9000	2.0000	1.8000	#VALUE!		1.9333	
Inner diameter		.0320	.0320	.0320	.0320	.0320		.0320	
Outer diameter		.0365	.0365	.0365	.0365	.0365		.0365	
E (4PT)		272300	254400	267800	241100	#VALUE!		258900	

PEEK/AIR/55"

Description	PEEK
Lot #	AIR GAP FOR DIE 55"
Operator and date	LARRY WASICEK 5/19/94

Enter in moment weight	0.045
Enter in inherent weight	0.005
Enter in span	0.5

Note:
Inherent weight is .1 for 6" machine
Inherent weight is .005 for 1" machine

Raw Bending Data

samples

		#1	#2	#3	#4	#5		Avg.	Std.Dev.
	0	1	1	1	1		0	1.0	0.0
	3	7	7	7	7		3	7.0	0.0
Degrees	6	13	13	12	14		6	13.0	0.8
	9	18	20	18	19		9	18.8	1.0
	12	23	24	22	24		12	23.3	1.0
	15	27	27	27	28		15	27.3	0.5
Kink angle		30	30	28	32			30.0	1.6
Slope (3,6,9) ref.		1.8333	2.1667	1.8333	2.0000	#VALUE!		1.9583	
Slope (0,3,6,9)		1.9000	2.1000	1.8667	2.0333	#VALUE!		1.9750	

Inner diameter	.0340	.0340	.0340	.0340		.0340
Outer diameter	.0380	.0380	.0380	.0380		.0380

E (4PT)	246800	272800	242500	264100	#VALUE!	256500

PEEK/ACUTEK

Description	PEEK
Lot #	ACUTEK
Operator and date	LARRY WASICEK 5/19/94

Enter in moment weight	0.045
Enter in inherent weight	0.005
Enter in span	0.5

Note:
Inherent weight is .1 for 6" machine
Inherent weight is .005 for 1" machine

Raw Bending Data

	samples							
	#1	#2	#3	#4	#5		Avg.	Std.Dev.
0	1	1	1			0	1.0	0.0
3	14	14	14			3	14.0	0.0
degrees 6	27	27	24			6	26.0	1.7
9	40	40	39			9	39.7	0.6
12	50	50	50			12	50.0	0.0
15	60	60	60			15	60.0	0.0
Kink angle	81	80	76					
Slope (3,6,9) ref.	4.3333	4.3333	4.1667	#VALUE!	#VALUE!		4.2778	
Slope (0,3,6,9)	4.3333	4.3333	4.1333	#VALUE!	#VALUE!		4.2667	
Inner diameter	.0325	.0325	.0325				.0325	
Outer diameter	.0400	.0400	.0400				.0400	
E (4PT)	291800	291800	278400	#VALUE!	#VALUE!		287300	